

Amendments to Claims

1. (Currently Amended) A process for preparing a low color, polyvinyl butyral sheet for use in the manufacture of glass laminates comprising the steps:

(I) admixing polyvinyl alcohol, butyraldehyde, an acid or mixture of acids, water, and ~~a surfactant selected from the group consisting of organic bisulfites, inorganic bisulfites and sulfosuccinates~~ sodium dialkyl sulfosuccinate;

(II) stabilizing the mixture obtained in step (I) by (a) raising the pH of the mixture to at least pH 10, (b) isolating the polyvinyl butyral resin composition by draining the liquid, and (c) washing the polyvinyl butyral resin composition with neutral pH water;

(III) plasticizing the polyvinyl butyral resin composition with from about 30 to about 50 pph of plasticizer selected from the group consisting of triethylene glycol di(2-ethylhexanoate), tetraethylene glycol diheptanoate, dibutyl sebacate, and mixtures thereof, based on the dry weight of the resin;

(IV) mixing (a) a polyvinyl butyral bleaching compound selected from the group consisting of organic bisulfites, inorganic bisulfites and sulfosuccinates, and, optionally, (b) an antioxidant and a UV light stabilizer with the polyvinyl butyral resin composition; and

(V) extruding the polyvinyl butyral resin composition at a temperature of from about 175°C to about 225°C to obtain a polyvinyl butyral sheet having a glass transition temperature (T_g) of greater than about 32°C and a YID of less than about 12.

2. (Previously presented) The process of Claim 1 wherein the process comprises the mixing with the antioxidant and the UV light stabilizer.

3. (Cancelled)

4. (Cancelled)

5. (Cancelled)

6. (Cancelled)

7. (Cancelled)

8. (Cancelled)

9. (Cancelled)
10. (Cancelled)
11. (Previously presented) The process of Claim 26 wherein the polyvinyl butyral is plasticized using a wet process.
12. (Previously presented) The process of Claim 26 wherein the polyvinyl butyral is plasticized using a dry process.
13. (Cancelled)
14. (Cancelled)
15. (Cancelled)
16. (Cancelled)
17. (Cancelled)
18. (Cancelled)
19. (Cancelled)
20. (Cancelled)
21. (Cancelled)
22. (Cancelled)
23. (Cancelled)
24. (Cancelled)
25. (Cancelled)
26. (Currently Amended) A process for preparing a low color, polyvinyl butyral sheet for use in the manufacture of glass laminates comprising the steps:
 - (I) admixing polyvinyl alcohol, butyraldehyde, an acid or mixture of acids, water, and sodium ~~dialkyl~~ dioctyl sulfosuccinate;
 - (II) stabilizing the mixture obtained in step (I) by (a) raising the pH of the mixture to at least pH 10, (b) isolating the resin by draining the liquid, and (c) washing the resin with neutral pH water;
 - (III) plasticizing the polyvinyl butyral resin composition with from about 30 to about 50 pph of plasticizer, based on the dry weight of the polyvinyl butyral resin, wherein the plasticizer is selected from the group consisting of

triethylene glycol di(2-ethylhexanoate),
tetraethylene glycol diheptanoate, dibutyl
sebacate, and mixtures thereof; and

- (IV) extruding the polyvinyl butyral resin composition
at a temperature of from about 175°C to about
225°C to obtain a polyvinyl butyral sheet having
a glass transition temperature (T_g) of greater
than about 32°C and a YID of less than about 12.

27. (Cancelled)

28. (Currently Amended) The process of Claim ~~24~~ 1
wherein the ~~surfactant~~ sodium dioctyl sulfosuccinate is
included in amount of from about 0.01 to about 0.85 pph by
weight, based on the weight of polyvinyl alcohol.

29. (Cancelled)

30. (Currently Amended) The process of Claim ~~27~~ 26
wherein the sodium dioctyl sulfosuccinate is included in amount
of from about 0.01 to about 0.85 pph by weight, based on the
weight of polyvinyl alcohol.

31. (Currently Amended) The process of Claim ~~24~~ 1
wherein the ~~surfactant~~ sodium dioctyl sulfosuccinate is
included in amount of from about 0.10 to about 0.80 pph by
weight, based on the weight of polyvinyl alcohol.

32. (Cancelled)

33. (Currently Amended) The process of Claim ~~27~~ 26
wherein the sodium dioctyl sulfosuccinate is included in amount
of from about 0.10 to about 0.80 pph by weight, based on the
weight of polyvinyl alcohol.

34. (Cancelled)

35. (Previously Presented) The process of Claim 26
further comprising mixing an antioxidant and a UV light
stabilizer with the polyvinyl butyral resin composition after
the plasticizing and prior to the extruding.

36. (Previously presented) The process of Claim 35
wherein the antioxidant is included in an amount of from about
0.01 to about 0.6%, based on the total weight of the sheet.

37. (Previously presented) The process of Claim 36
wherein the antioxidant is a bis-phenolic antioxidant.

38. (Previously presented) The process of Claim 36 wherein the antioxidant is present in amount of from about 0.03 to about 0.3%, based on the total weight of the sheet.

39. (Previously presented) The process of Claim 38 wherein the antioxidant is a bis-phenolic antioxidant selected from the group consisting of 2,2'-ethylidenebis(4,6-di-t-butylphenol); 4,4'-butylidenebis(2-t-butyl-5-methylphenol); 2,2'-isobutylidenebis(4,6-dimethylphenol); and 2,2'-methylenebis(6-t-butyl-4-methylphenol).

40. (Currently Amended) The process of Claim ~~24~~ 26 wherein the YID is less than about 8.

41. (Previously Presented) The process of Claim 2 wherein the bleaching compound is a sodium dialkyl sulfosuccinate.

42. (Cancelled)

43. (Cancelled)

44. (Cancelled)

45. (Cancelled)

46. (Previously presented) The process of Claim 1 wherein the polyvinyl butyral bleaching compound is selected from the group consisting of sodium or potassium bisulfite, and tetramethylammonium bisulfite.

47. (Previously presented) The process of Claim 1 wherein the polyvinyl butyral bleaching compound is present in an amount of from about 0.01 to about 0.85 parts per hundred, based on the weight of polyvinyl alcohol used in the preparation of the polyvinyl butyral resin composition.

48. (Previously presented) The process of Claim 1 wherein the polyvinyl butyral bleaching compound is present in an amount of from about 0.10 to about 0.75 parts per hundred, based on the weight of polyvinyl alcohol used in the preparation of the polyvinyl butyral resin composition.

49. (Previously presented) The process of Claim 1 wherein the plasticizer is triethylene glycol di(2-ethylhexanoate).

50. (Currently Amended) The process of Claim ~~24~~ 38 wherein the plasticizer is triethylene glycol di(2-ethylhexanoate).

51. (Previously presented) The process of Claim 26 wherein the plasticizer is triethylene glycol di(2-ethylhexanoate).

52. (Currently Amended) The process of Claim ~~32~~ 33 wherein the plasticizer is triethylene glycol di(2-ethylhexanoate) and is present in an amount of from about 30 to about 45 pph, by weight, based on the dry weight of the polyvinyl butyral resin.

53. (Previously presented) The process of Claim 52 further comprising the mixing the antioxidant and the UV light stabilizer with the polyvinyl butyral resin composition, wherein the antioxidant is included in an amount of from about 0.01 to about 0.6%, based on the total weight of the sheet, and wherein the antioxidant is a bis-phenolic antioxidant.

54. (Currently Amended) The process of Claim ~~24~~ 26 wherein the admixing is carried out at a temperature of 5 to 100°C.

55. (Previously presented) The process of Claim 52 wherein the admixing is carried out at a temperature of about 90°C.

56. (Cancelled)

57. (Cancelled)

58. (Previously Presented) The process of Claim 1 wherein the plasticizer is the triethylene glycol di(2-ethylhexanoate).

59. (Previously Presented) The process of Claim 58 wherein the polyvinyl butyral bleaching compound is selected from the organic bisulfites.

60. (Previously Presented) The process of Claim 58 wherein the polyvinyl butyral bleaching compound is selected from the inorganic bisulfites.

61. (Previously Presented) The process of Claim 58 wherein the polyvinyl butyral bleaching compound is selected from the sulfosuccinates.

62. (Previously Presented) The process of Claim 58 wherein the polyvinyl butyral bleaching compound is sodium dialkyl sulfosuccinate.

63. (Previously Presented) The process of Claim 58 wherein the bleaching compound is sodium dioctyl sulfosuccinate.

64. (Previously Presented) The process of Claim 1 wherein the plasticizer is the tetraethylene glycol diheptanoate.

65. (Previously Presented) The process of Claim 1 wherein the plasticizer is the dibutyl sebacate.

66. (Currently Amended) A process for preparing a low color, polyvinyl butyral sheet for use in the manufacture of glass laminates comprising the steps:

- (I) admixing polyvinyl alcohol, butyraldehyde, an acid or mixture of acids, water, and sodium dialkyl sulfosuccinate ~~a surfactant selected from the group consisting of organic bisulfites, inorganic bisulfites and sulfosuccinates;~~
- (II) stabilizing the mixture obtained in step (I) by (a) raising the pH of the mixture to at least pH 10, (b) isolating the resin by draining the liquid, and (c) washing the resin with neutral pH water;
- (III) plasticizing the polyvinyl butyral resin composition with from about 30 to about 50 pph of plasticizer selected from the group consisting of diesters obtained by (a) the reaction of triethylene glycol or tetraethylene glycol with aliphatic carboxylic acids having from 6 to 10 carbon atoms and (b) the reaction of sebacic acid with aliphatic alcohols having from 1 to 18 carbon atoms, and mixtures thereof, based on the dry weight of the polyvinyl butyral resin; and
- (IV) extruding the polyvinyl butyral resin composition at a temperature of from about 175°C to about 225°C to obtain a polyvinyl butyral sheet having a glass transition temperature (T_g) of greater than about 32°C and a YID of less than about 12.

67. (Previously Presented) The process of Claim 66 wherein the plasticizer is selected from the group consisting of the diesters obtained by the reaction of triethylene glycol

or tetraethylene glycol with aliphatic carboxylic acids having from 6 to 10 carbon atoms.

68. (Cancelled)

69. (Previously Presented) The process of claim 1 further comprising laminating the polyvinyl butyral sheet to glass.

70. (Currently Amended) The process of claim ~~10~~ 28 further comprising laminating the polyvinyl butyral sheet to glass.

71. (Cancelled)

72. (Currently Amended) The process of claim ~~25~~ 38 further comprising laminating the polyvinyl butyral sheet to glass.

73. (Previously Presented) The process of claim 26 further comprising laminating the polyvinyl butyral sheet to glass.

74. (Currently Amended) The process of claim ~~29~~ 30 further comprising laminating the polyvinyl butyral sheet to glass.

75. (Previously Presented) The process of claim 46 further comprising laminating the polyvinyl butyral sheet to glass.

76. (Previously Presented) The process of claim 66 further comprising laminating the polyvinyl butyral sheet to glass.

77. (New) The process of claim 1 further comprising forming a windshield by laminating the polyvinyl butyral sheet to glass.

78. (New) The process of claim 26 further comprising forming a windshield by laminating the polyvinyl butyral sheet to glass.

79. (New) The process of claim 66 further comprising forming a windshield by laminating the polyvinyl butyral sheet to glass.

80. (New) The process of claim 1 further comprising forming a glass laminate for use in a home or other building. to glass.

81. (New) The process of claim 26 further comprising forming a glass laminate for use in a home or other building. to glass.

82. (New) The process of claim 66 further comprising forming a glass laminate for use in a home or other building. to glass.